

**POLYPROPYLENE RESIN COMPOSITION FOR AUTOMOBILE COMPONENT PART**

**Patent number:** JP9165478  
**Publication date:** 1997-06-24  
**Inventor:** MORITA HIDEYO; SANO YUTAKA; TODO SUMIO;  
TAKASAKI YASUBUMI  
**Applicant:** UBE IND LTD  
**Classification:**  
- international: C08L23/10; C08K3/00; C08K3/26; C08K3/36  
- european:  
**Application number:** JP19950326723 19951215  
**Priority number(s):**

**Abstract of JP9165478**

**PROBLEM TO BE SOLVED:** To prepare a resin compsn. for an automobile component part which has excellent dimming resistance, heat aging resistance, moldability and other properties by adding a particular additive to a composition comprising a crystalline polypropylene, an inorganic filler, and a rubber.

**SOLUTION:** A crystalline polypropylene (A) in an amt. of 50 to 95wt.%, 5 to 60wt.% inorganic filler (B) (e.g. talc), and 0 to 20wt.% rubber (C) (e.g. ethylene/propylene rubber) are mixed together. Subsequently, to the resultant compsn. in an amt. of 100 pts.wt. are added 0.01 to 5 pts.wt. antioxidant (D) having a percentage wt. reduction at 250 deg.C of not more than 5wt.% [e.g. tris(3,5- di-tert-butyl-4-hydroxybenzyl)isocyanurate], 0.01 to 5 pts.wt. epoxy resin (E), 0.001 to 1 pt.wt. hydrotalcite (F), 0.01 to 5 pts.wt. silicone oil, a low mol.wt. polyolefin having a hydroxyl group or polyethylene wax (G), and 0.01 to 5 pts.wt. synthetic silica (H), thus preparing a polypropylene resin compsn. for an automobile component.

---

Data supplied from the **esp@cenet** database - Worldwide